

# BELLFINE MG *Technical Information*

MG-405L	Properties		
	Contact us.		

MG-407S	Properties		
	Pellet Dia [mm $\phi$ ]	0.7~0.8	
	Packing Density [g/ml]	0.74	
	Hardness (JIS-method) [wt%]	96	
	N <sub>2</sub> PSA performance		
	N <sub>2</sub> Purity [%]	Productivity [Nm <sup>3</sup> /h/t]	Air/N <sub>2</sub>
	99.99	160	4.0
99.9	240	3.1	
99	360	2.4	

MG-7L3	Properties		
	Pellet Dia [mm $\phi$ ]	1.0~1.8	
	Packing Density [g/ml]	0.68	
	Hardness (JIS-method) [wt%]	96	
	N <sub>2</sub> PSA performance		
	N <sub>2</sub> Purity [%]	Productivity [Nm <sup>3</sup> /h/t]	Air/N <sub>2</sub>
	99.99	110	4.7
99.9	190	3.8	
99	330	2.6	

※ Adsorption Pressure 0.8MPa  
 Temperature 20°C  
 Adsorption Time 30~40sec